



HAL
open science

The kinetics of silica-based fiber radioluminescence for pulsed-radiation dosimetry

Marjorie Grandvillain, Marie Vidal, Petter Hofverberg, Hicham El Hamzaoui, Mohamed Bouazaoui, Bruno Capoen, Joël Herault, Mourad Benabdesselam, Franck Mady

► **To cite this version:**

Marjorie Grandvillain, Marie Vidal, Petter Hofverberg, Hicham El Hamzaoui, Mohamed Bouazaoui, et al.. The kinetics of silica-based fiber radioluminescence for pulsed-radiation dosimetry. 20th International Conference on Solid State Dosimetry, Sep 2023, Viareggio, Italy. hal-04584640

HAL Id: hal-04584640

<https://hal.univ-cotedazur.fr/hal-04584640v1>

Submitted on 23 May 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution 4.0 International License

The kinetics of silica-based fiber radioluminescence for pulsed-radiation dosimetry.

Marjorie Grandvillain^{1,2*}, Marie Vidal², Petter Hofverberg², Mohamed Bouazaoui³, Hicham El Hamzaoui³, Bruno Capoen³, Joël Hérault², Mourad Benabdesselam¹, Franck Mady¹

1 Université Côte d'Azur, Fédération de recherche Claude Lalanne, Institut de Physique de Nice, CNRS UMR7010, 17 rue Julien Lauprêtre, 06200 Nice, France

2 Centre Antoine Lacassagne, Fédération de recherche Claude Lalanne, 227 avenue de la Lanterne, 06200 Nice, France

3 Université Lille, CNRS, UMR8523 - PhLAM – Physique des Lasers, Atomes et Molécules, CERLA/IRCICA, F-59000 Lille, France

* Corresponding author :marjorie.grandvillain@univ-cotedazur.fr

Abstract:

New radiotherapy techniques, as those using flash irradiations, requires developing innovative dosimeters capable of measuring high, pulsed dose rates. Our FIDELIO project aims at developing miniaturized silica fiber-based RL dosimeters optimized for pulsed photon and proton beams. The proportionality of their RL plateau level to dose rate is well established and is no longer an issue. Critical problems for pulse dosimetry, much less addressed, rather concern RL rise and fall times and the stability of the RL response over time and cumulated dose. We studied these characteristics experimentally for Gd³⁺- and Ce³⁺-doped silica fibers. The probes, 1 cm long and 220 μm in diameter, were connected to a photodetector through radiation-hard silica fibers. They were irradiated under 30kV X rays (pre-clinical investigations) at dose rate 0.8-11.3 Gy/s, but also in the 65 and 226 MeV proton beams of the anti-cancer center of Nice. To identify the parameters affecting RL kinetics and stability, we also used a model suited to rare-earth-doped silica glasses including a quasi-continuous distribution of traps and a single type of recombination centers. To study the effect of short exposure times on RL kinetics, 1 to 10 s X-ray irradiations were sequentially applied at constant dose rate, separated by rest periods of 10 s. As exposure time increases along successive irradiations, the rise time of the RL is only slightly changed and the RL plateau remains stable. An increasing phosphorescence is however observed between irradiations for both Ce and Gd-doped probes, due to a slower and slower phosphorescence decay. This observation is reproduced by simulation and shown to be due to detrapping from “shallow” traps, whose depth is around a demarcation level that continuously sinks into the bandgap with time. As a complement to simulations, analysis of the model in two limit cases (no trapping and trapping without detrapping) allowed us to establish formal solutions between which all real cases lie. Important properties are thus demonstrated: 1) The minimum rise time corresponds to the ‘no trapping’ case, which is in fact a case with trapping but undelayed (instant) detrapping. Inversely proportional to the square root of the dose rate, it is about a few tens of microseconds at 10 Gy s⁻¹; 2) The ‘no detrapping’ case leads to the longest rise time which is inversely proportional to the dose rate. It can reach hundreds of seconds at 10 Gy s⁻¹; 3) Detrapping from shallow traps shortens rise time while increasing fall time. Pre-existing filling of these traps, determined by previous doses and time elapsed since them, unavoidably impacts RL kinetics without affecting its plateau; 5) Regardless of detrapping delay, the initial RL growth (at much smaller times than the rise time) is always proportional to the square of the dose rate. This offers opportunities for efficient, radiative-history independent, pre-plateau dose rate assessment for short pulse dosimetry.